



Bitumen C240

(Viscosity Grade Bitumen)

PRODUCT DATA SHEET

Bitumen Class 240 or C240 is a viscosity-graded bitumen with a viscosity of 240 Poise at 60°C. Bitumen Class 240 is designed for use in environments that require a higher resistance to deformation, especially under heavy traffic and in regions with warmer climates.

CHARACTERISTICS	UNIT	LIMITS	TEST METHODS
Viscosity at 60°C	Pa.s	190-280	ASTM D2171
Viscosity at 135°C	Pa.s	0.32-0.55	ASTM D2170
Penetration @25°C (77°F), 100gm, 5sec	0.1MM	Min. 53	ASTM D5
Flash Point Cleveland open cup	°C	Min. 250	ASTM D92
Matter insoluble in toluene	%Wt	Max. 1.0	ASTM D4072
Tests on residue from thin-film oven test:			
Viscosity of residue at 60°C as % of original	%	Max. 300	ASTM D2171

Quality:

The quality of the bitumen is assured for every delivery with arrangement of international inspector to check quality and controlling the production by Quality Control and also by batch test report before shipping

Application:

Bitumen Class 240 is primarily used in high-traffic, heavy-load environments, including highways, industrial roads, airports, and areas with warm climates. Its resistance to deformation and stability under heat make it ideal for demanding applications where heavy-duty performance is essential.

Asphalt Recommendations:

Mixing Temperature: 140-165°C

Spraying Temperature: 170-180°C

Health & Safety:

Bitumen is unlikely to present any significant health or safety hazard when properly used in the recommended application where good standards of industrial practice are maintained.

Packaging:

New steel drums, reconditioned steel drums, poly bags. Bulk;
Steel Drums: 180Kg, 200Kg
Poly Bags: 300Kg, 1000Kg
Bulk: Tank Container

Code Approvals/Compliance:

Meets AS2008-2013

Learn More [↗](#)

www.nuroil.com

For further information, please contact:

Nuroil Trading FZE

Email : info@nuroil.com

Phone : +971 55 8405476

Disclaimer: The information contained herein is based on our current knowledge of the underlying data and is intended to describe the product for the purpose of health, safety and environmental requirements only. No warranty or guarantee is expressed or implied regarding the accuracy of these data or the results to be obtained from the use of the product.