



# Bitumen RC800

(Cutback Bitumen Rapid-Curing)

## PRODUCT DATA SHEET

Cutback Bitumen Rapid Curing 800 (RC-800) is a type of cutback bitumen that is blended with a fast-evaporating petroleum solvent, which reduces its viscosity for easier application. Cutback Bitumen RC-800's combination of moderate viscosity and rapid curing capabilities makes it ideal for various road construction and maintenance projects where durability and quick application are essential.

CHARACTERISTICS	UNIT	LIMITS	TEST METHODS
Kinematic Viscosity at 60°C	mm <sup>2</sup> /s	800-1600	ASTM D-2170
Flash Point (Tag Open-Cup), Min	°C	Min. 27	ASTM D-1310
<b>DISTILLATION TEST: (Distillate, Volume Percent of Total Distillate to 360°C)</b>			
To 190°C	% Vol.	-	ASTM D-402
To 255°C	% Vol.	Min. 15	ASTM D-402
To 260°C	% Vol.	Min. 45	ASTM D-402
To 316°C	% Vol.	Min. 75	ASTM D-402
Residue from distillation to 360°C, by difference	% Vol.	Min. 75	ASTM D-402
<b>TEST ON RESIDUE FROM DISTILLATION:</b>			
Viscosity at 60°C	Pa.s	60-240	ASTM D2171
Ductility at 25°C	CM	Min. 100	ASTM D-113
Solubility in Trichloroethylene	% Wt	Min. 99	ASTM D-2042
Water	% Wt	Max. 0.2	ASTM D-95

### Quality:

The quality of the bitumen is assured for every delivery with arrangement of international inspector to check quality and controlling the production by Quality Control and also by batch test report before shipping.

### Application:

Cutback Bitumen RC-800's combination of moderate viscosity and rapid curing capabilities makes it ideal for various road construction and maintenance projects where durability and quick application are essential.

For **Tack Coat** apply at a rate of 0.2 to 0.4 liters per square meter (L/m<sup>2</sup>).

For **Prime Coat** apply at a rate of 0.8 to 1.5 liters per square meter (L/m<sup>2</sup>).

### Health & Safety:

Bitumen is unlikely to present any significant health or safety hazard when properly used in the recommended application, provided good standards of industrial and personal hygiene are maintained.

For further information, please contact:

### Nuroil Trading FZE

Email : [info@nuroil.com](mailto:info@nuroil.com)

Phone : +971 55 8405476

### Packaging & Storage:

New steel drums, reconditioned steel drums or IBC Tanks

Steel Drums : 200Ltrs

IBC Tank : 1000Ltrs

Storage life is excellent when stored in an airtight container. It is recommended to recirculate the product at least every 14 days during storage in large bulk tanks.

### Code Approvals/Compliance:

Meets: ASTM D2028 or AASHTO M81-92 2008, IS: 217 – 1988

### Learn More

[www.nuroil.com](http://www.nuroil.com)