Oxidized Bitumen 95/40



(Blown Bitumen)

Oxidized Bitumen 95/40 (also known as Blown Bitumen 95/40) is a specialized grade of bitumen produced by blowing air through bitumen at high temperatures, resulting in a material with enhanced properties.

| CHARACTERISTICS | UNIT | LIMITS | TEST METHODS |
|--|-------|-----------|--------------|
| Penetration @25°C (77°F), 100gm, 5sec | 0.1MM | 30-40 | ASTM D5 |
| Softening Point °C | °C | 90-100 | ASTM D36 |
| Ductility @25°C, 5 cm/min | СМ | Min. 1.5 | ASTM D113 |
| Solubility in CS ₂ | %Wt | Min. 99 | ASTM D4 |
| Flash Point Cleveland open cup | °C | Min. 260 | ASTM D92 |
| Specific Gravity at 25°C | - | 1.00-1.05 | ASTM D70 |
| After Rolling Thin-Film Oven Test (RTFO) | | | |
| Loss on Heating | %Wt | 0.2 | ASTM D6 |

Quality:

The quality of the bitumen is assured for every delivery with arrangement of international inspector to check quality and controlling the production by Quality Control and also by batch test report before shipping.

Application:

Oxidized bitumen 95/40 is ideal for applications that require high temperature stability, durability, and excellent waterproofing capabilities, making it valuable in infrastructure, industrial, and marine settings.

Health & Safety:

Bitumen is unlikely to present any significant health or safety hazard when properly used in the recommended application, provided good standards of industrial and personal hygiene are maintained.

Packaging:

New steel drums, reconditioned steel drums or eco-friendly Weatherproof packaging in poly bags, Kraft bag Steel Drums : 180Kg, 200Kg Jumbo Bag : 1000Kg Others : 25kg Kraft/PP Bag, Metal Pails, Carton Box

Code Approvals/Compliance: Meets BS EN 13304-2009

Learn More C www.nuroil.com

For further information, please contact: **Nuroil Trading FZE** Email : info@nuroil.com Phone : +971 55 8405476

Disclaimer: The information contained herein is based on our current knowledge of the underlying data and is intended to describe the product for the purpose of health, safety and environmental requirements only. No warranty or guarantee is expressed or implied regarding the accuracy of these data or the results to be obtained from the use of the product.